



# EKOAKVA, EKOAKVA M

## WATER-BASED ACRYLIC LACQUERS



- Fast drying
- May be used for finish of wooden and various mineral surfaces

### **DESCRIPTION:**

Single-component water-based acrylic lacquers.

### **FIELD OF APPLICATION:**

Lacquers are intended be used for lacquering of indoor wooden and mineral surfaces (concrete, plaster and brick) not exposed to intense mechanical wear (for example, walls). Not suitable for floors.

### **TECHNICAL PARAMETERS:**

<b><u>Colour/appearance</u></b>	Lacquers are semi-transparent during the application, but become fully transparent in the process of drying (in approximately 30 minutes). The varnishes may be tinted by RILAKOLOR tinting system using COLTEC WOOD catalogue (75 shades).
<b><u>Gloss:</u></b>	EKOAKVA – semi-transparent, EKOAKVA M – semi-matte.
<b><u>Drying time at 20°C temperature:</u></b>	1 hour
<b><u>Consumption:</u></b>	8÷10 m <sup>2</sup> /l for one layer.
<b><u>Solvent:</u></b>	Water
<b><u>Tools used for application:</u></b>	Brush, roller, paint sprayer.
<b><u>Storage period:</u></b>	36 months in tightly closed manufacturer's container at the temperature exceeding 0°C.
<b><u>Packaging:</u></b>	0.9 l; 2.7 l; 10 l.

## **APPLICATION:**

### **PREPARATION OF VARNISH FOR USE:**

Mix lacquer well before use. Dilute with water till required viscosity, if necessary.

### **PREPARATION OF SURFACE:**

Remove dirt and dust from the surfaces to be lacquered.

**VARNISHING:**

Apply varnish to clean and dry surfaces in 2-3 layers. Temperature of air and varnished surface must not be lower than +5°C, relative air humidity – not higher than 80%.

Attention has to be paid while varying thickness of coat. Thicker coats tend to produce higher hiding effect. Trials on small experimental area are recommended to be premerger prior to painting of whole area.

**TOOL CLEANING:**

Use water for cleaning of used tools.

**ENVIRONMENT AND OCCUPATIONAL SAFETY AND HEALTH PROTECTION:**

Keep out of reach of children. Avoid breathing dust/fume/gas/mist/vapours/spray. IF SWALLOWED: Call a POISON CENTER or doctor/physician if you feel unwell. IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.



0.9l, 2.7l, 10l

8÷10 m<sup>2</sup>/l

1 h

RILAKOLOR  
(EC BASE)